

20-5-24/60

The Synthesis of Polyorganoaluminum Siloxanes. Exchange Decomposition Reaction Between Sodium Salts of Alkyl-Silanetriols and Aluminum Chloride.

organic solvents. The investigations showed that on the occasion of the interaction of chloroaluminum with sodium salts of phenyl-silantriol, ethyl-silantriol and with the disodium salt of 1,3,5-triphenyl-1,3,5-trimethyl silanoxane, the formation of the substances mentioned in the title proceeds according to pattern: $C_6H_5Si(OH)_2ONa + AlCl_3 \rightarrow C_6H_5Si(O)_2O/3Al + nH_2O$. The resulting polymers represent solid, brittle, glass-like substances, soluble in benzene, alcohol and acetone. On the occasion of the evaporation of their solutions there develop transparent films on solid surfaces. The sodium salts of alkyl-silanetriols used by the authors in the exchange decomposition reaction, were synthesized by the influence of an equimolecular amount of caustic soda upon polyorganoaluminum siloxanes. These sodium salts represent solid crystalline substances containing crystallization water. According to the amount of crystallization water these substances are soluble in alcohol and acetone. Experimental part with the usual data. (3 Slavic references.) Institute for Elementary-Organic Compounds of the Academy of Science of the U.S.S.R.

ASSOCIATION PRESENTED BY SUBMITTED AVAILABLE Card 2/2

Library of Congress.

ZHDANOV, A. A., ANDRIANOV, K. A.,

"The Synthesis of Polyorganometalosiloxanes and the Investigation of their properties," paper submitted at the Symposium on Organic and Nonsilicate Silicon Chemistry on 12th-14th May 1958, Dresden.

1. The reaction of metals- sodium, magnesium and aluminum- with organosilanols- diethylsilanediol, 1,3-dihydroxytetraethyl- disiloxane and polyphenylsiloxane resins, is under investigation. It will be shown that the above compounds react with the metals under anhydrous conditions with the formation of metal-siloxane (metal-oxygen-silicon) linkages.
2. The reactivity of the silanols is dependent on the stability of their hydroxyl groups. Compounds which easily undergo condensation do not react with metals. Compounds which have stable hydroxyl groups react easily with metals.
3. It will be shown that by the action of aluminum chloride on the sodium salts of phenyl- and ethylsilanetriols and of 1,3,5-trimethyl-1,3,5-triphenyltrisiloxane, polymers are formed- the polyorganoaluminosiloxanes.

Abstract: B-3,108,944 (Encl.)

ZHDANOV, A. A. and ANDRIANOV, K. A.

"Organosiloxyaluminoxane"

paper submitted for the Symposium on Organic and Non-Siliceous Silicon Chemistry,
Dresden, 12-14 May 1958.

ZHDANOV, A. A.
ANDRIANOV, K. A. and ZHDANOV, A. A.

"Synthese von Neuen Polymeren Met anorganischen Kettenmolekullen,"

paper presented at the Intl. Symposium on Macromolecular Chemistry, Prague, ~~1957~~
9-15 Sep 1957.

Inst. Organic Chemistry im Zelinskiy, AS USSR

Kautschuk und Gumi, No. 1, 1958.

SOV/62-58-6-24/37

AUTHORS: Andrianov, K. A., Zhdanov, A.A.

TITLE: The Synthesis of Tetrakis-(Triethyl-siloxy) Titanium and Tetrakis-(Triethylsiloxy)-Tin (Sintez tetrakis-(triethylsiloksi) titana i tetrakis (triethylsiloksi) olova)

PERIODICAL: Izvestiya Akademii nauk SSSR, Otdeleniye khimicheskikh nauk, 1958, Nr 6, pp. 779-780 (USSR)

ABSTRACT: The synthesis of silicon-organic titanium derivatives are dealt with by several scientific papers. In the course of the present report the authors describe the synthesis of triethylsiloxy titanium and tetratriethylsiloxy tin brought about by the exchange reaction of sodium-triethylsilylanolate with tetrachlorotitanium and zinc chloride:

$$4(C_2H_5)_3SiONa + SnCl_4 \rightarrow [(C_2H_5)_3SiO]_4Sn + 4NaCl.$$
Further data relating to the investigation of the reaction as well as to the interaction between sodium triethylsilylanolate and other halides are intended to be discussed by the authors in a paper to follow. There are 5 references, 3 of which are Soviet.

Card 1/2

The Synthesis of Tetrakis-(Triethyl-siloxy)
Titanium and Tetrakis-(Triethylsiloxy)-Tin.

SOV/62-58-6-24/37

ASSOCIATION: Institut elementoorganicheskikh soedineniy Akademii nauk
SSSR (Institute of Elemental-organic Compounds AS USSR)

SUBMITTED: January 21, 1958

1. Metalorganic compounds--Synthesis 2. Titanium--Chemical
reactions 3. Tin--Chemical reactions 4. Silicon compounds
(Organic)--Chemical reactions 5. Zinc chloride--Chemical reactions

Card 2/2

AUTHORS: Andrianov, K. A., Zhdanov, A. A. SOV/62-58-9-9/26

TITLE: The Reaction of Metals With Hydroxyl-Containing Organosilicon Compounds (O vzaimodeystvii metallov s gidroksil-soderzhashchimi kremneorganicheskimi soyedineniyami)

PERIODICAL: Izvestiya Akademii nauk SSSR. Otdeleniye khimicheskikh nauk, 1958, Nr 9, pp 1076 - 1079 (USSR)

ABSTRACT: In the previous papers the authors showed that triethylsilanol can react with aluminum to form aluminum triethylsilanolate with the liberation of hydrogen. The high reactivity of hydroxyl-containing organosilicon compounds toward metals can only be explained by the fact that the silicon atom in these compounds exhibits a high degree of polarizability. The authors were interested in investigating the reactivity of several polymers of organosilicon compounds which had hydroxyl groups at the silicon atom. It was found that in the reaction of these compounds with metallic sodium, magnesium, and aluminum that hydrogen was liberated and a metal siloxane was formed. The reactivity of the siloxy-con-

Card 1/2

The Reaction of Metals With Hydroxyl-Containing
Organosilicon Compounds

SOV/62-58-9-9/26

taining organosilicon compounds depends upon the resistivity at these hydroxyl groups. Compounds which enter into intermolecular condensation reactions easily do not react with metals. On the other hand, hydroxyl groups which are resistive to condensation reactions react relatively easily with metals. There are 6 tables and 4 references, 2 of which are Soviet.

ASSOCIATION: Institut elementoorganicheskikh soyedineniy Akademii nauk
SSSR (Institute of Elemental-organic Compounds, AS USSR)

SUBMITTED: February 5, 1957

Card 2/2

AUTHORS: Andrianov, K. A., Corresponding Member of the AS USSR, Zhdanov, A. A., Asnovich, E. Z. 20-118-6-21/43

TITLE: On the Synthesis of Infusible but Soluble Polymers (O sinteze neplavkikh, no rastvorimykh polimerov)

PERIODICAL: Doklady Akademii Nauk SSSR, 1958, Vol. 118, Nr 6, pp. 1124-1127 (USSR).

ABSTRACT: The fusibility and solubility of polymers in organic solvents are considered to be dependent on the molecular structure of the chains. Polymers with a linear structure are soluble and meltable by heating, regardless of their molecular weight. The branching of the chain, viz. the formation of laced (ssbityya) structures and spatial structures makes the polymer lose these properties. This dependence concerns all polymers. The authors tested the synthesis of polymers which were readily soluble in non- or slightly-polar solvents but which did not melt when heated. The results obtained by thorough investigations show that no polymers with the aforesaid properties can be obtained with the production of cyclic poly-organo-siloxanes. A general composition of the polymers (C₆H₅SiO_{1,5})_x which cor-

Card 1/ 4

On the Synthesis of Infusible but Soluble Polymers

20-118-6-21/43

responds to a cyclic structure of the molecules, was proved during the hydrolysis of phenyltrichlorosilane. Such polymers, however, are soluble in organic solvents and melt when heated. A long lasting heating of the polyphenyl-siloxanes at 250°C and above causes an increase of the melting temperatures, but the polymer loses its solubility at the same time. The polymeric molecule grows apparently in first line due to bursting of the rings and their polymerization under the formation of structures which are laced. For increasing the melting-temperature of the complicated cyclic polyphenyl-siloxanes, aluminum was introduced into the molecule of the polymer. Aluminum-siloxane reacts with phenyl-trihydroxy-silane by precipitating water. A further condensation at the cost of the hydroxyl-groups under formation a polymer with a molecular weight of 5990, a content of hydroxyl-groups of 5,5% and a ratio Si: Al = 4,1. The obtained aluminum-phenyl-siloxane is a colorless, brittle, vitreous substance which does not melt with heating up to 500°C and does not sinter either (figure 1). It is readily soluble in: benzene, toluene, acetone, ethanol, chlorobenzene and carbon tetrachloride, yet insoluble in petroleum ether and white spirit. Though the content of OH-groups in the polymer decreases from 5,53 to 2,7% with a heating at 150°C for 10 hours (reference 1), its solubility remains un-

Card 2/4

On the Synthesis of Infusible but Soluble Polymers

20-1186-21/43

changed. The solubility in acetone is preserved also with heating at 200°C for 4 hours. With an action of heat of 300°C for 15 minutes, it is soluble in 85%. In the case of a longer lasting heating at 200°C and with a 15 minutes lasting heating at 400 and 500°C, the solubility gets completely lost. The constants and the chemical analysis (table 1) are given. An empirical formula for a term of the concerned polymer is given. A spatial structure of the polymeric molecule seems impossible, whereas such a term is a constituent of a complex cyclic or volumetric-polymeric molecule. Polyaluminum-ethylsiloxane was synthesized analogously. With equal properties as polyaluminum-phenylsiloxane it does not melt with heating (figure 1). The solubility of the former in various solvents at various temperatures is shown in table 1. Polyaluminum-ethylsiloxane loses its solubility more rapidly. An experimental part with usual data follows.

There are 1 figure, 1 table, and 2 references.

Card 3/4

On the Synthesis of Infusible but Soluble Polymers

20-118-6-21/43

ASSOCIATION: Institute for ^{Elementary} Organic Compounds, AS USSR
(Institut elementoorganicheskikh soyedineniy Akademii nauk SSSR)
All-Union Electrotechnical Institute imeni V. I. Lenin
(Vsesoyuznyy elektrotekhnicheskiy institut im. V. I. Lenina)

SUBMITTED: November 10, 1957.

Card 4/4

ZHDANOV, A. A.

A. A. Zhdanov and K. A. Andrianov, "The Synthesis of Polymers with Inorganic Chains."

Report presented at the Second All-Union Conference on the Chemistry and Practical Application of Silicon-Organic Compounds held in Leningrad from 25-27 September 1958.

Zhurnal prikladnoy khimii, 1959, Nr 1 pp 238-240 (USSR)

5(3)

AUTHOR:

Zhdanov, A. A., Candidate of Chemical Sciences

SOV/30-59-1-29/57

TITLE:

News in Brief (Kratkiye soobshcheniya) Scientific Conference on Organosilicon Compounds (Nauchnaya konferentsiya po kremniy-organicheskim soyedineniyam)

PERIODICAL:

Vestnik Akademii nauk SSSR, 1959, Nr 1, pp 115 - 117 (USSR)

ABSTRACT:

The conference was organized by the Association of German Chemists in Dresden (German Democratic Republic), May 12-14, 1958. Scientists from the following countries participated: the German Democratic Republic, the German Federal Republic, the USSR and Czechoslovakia. R. Müller (R. Myuller), (Dresden), director of the Institute for Organosilicon and Organofluorine Compounds reported in his opening address on the increasing scientific and technical importance of the investigated class of chemical compounds. F. Henglein (Karlsruhe) spoke about the synthesis of polymers containing groups the type of which is shown. G. Kolschütter (Darmstadt) dealt in his report with the investigation of the surfaces

Card 1/2

News in Brief. Scientific Conference on Organosilicon
Compounds

SOV/30-59-1-29/57

of compositions which form in the case of processing hydrated silicagel by the effect of trimethyl chlorosilane. The delegates of the Soviet Union D. N. Andreyev, M. G. Voronkov, A. A. Zhdanov, D. Ya. Zhinkin, N. S. Leznov, N. S. Nametkin, V. A. Ponomarenko reported on papers which had been published in Soviet periodicals already at an earlier time. After the conclusion of the conference R. Müller received the Soviet delegates and showed them the laboratories and equipment of the institute under his direction. They also undertook an excursion to Leipzig, Berlin and Potsdam which was organized by the Association of German Chemists.

Card 2/2

ANDRIANOV, K.A.; ZHDANOV, A.A.; ODINETS, V.A.

Condensation of silicon organic dicarboxylic keto acids with glycol. Vysokom.soed. 1 no.5:704-710 My '59.
(MIRA 12:10)

1. Institut elementoorganicheskikh soedineniy AN SSSR.
(Glycols) (Silicon organic compounds)

ANDRIANOV, K.A.; ZHDANOV, A.A.

Resistance of titanium, tin and aluminum triethylsiloxane derivatives to hydrolysis in the process of polymer formation. Vysokom. soed. 1 no.6:894-899 Je '59. (MIRA 12:10)

1. Institut elementoorganicheskikh soedineniy AN SSSR.
(Siloxanes) (Polymerisation)

5(3)

AUTHORS: Andrianov, K. A., Zhdanov, A. A., SOV/62-59-3-13/37
Kazakova, A. A.

TITLE: Synthesis of New Polymers With Inorganic Chains of Molecules
(Sintez novykh polimerov s neorganicheskimi tsepyami molekul)


PERIODICAL: Izvestiya Akademii nauk SSSR. Otdeleniye khimicheskikh nauk,
1959, Nr 3, pp 466-471 (USSR)

ABSTRACT: In the present paper some reactions of the formation of new
polymers with mineral chains of molecules containing aluminum,
titanium, phosphorus, and oxygen atoms were investigated.
By means of double decomposition of sodium ethyl silanolate
with titanium-tetrachloride as well as of sodium trimethyl
silanolate with titanium tetrachloride and aluminum chloride
dodecamethyl-titanoxy-tetrasiloxane, dodecaethyl-titanoxy-
tetrasiloxane and nonamethyl alumoxy-trisiloxane were syn-
thesized. In the investigation of the hydrolytic stability of
nonaethyl-alumoxy-trisiloxane it was found that during hydro-
lysis a simultaneous formation of polyorganosilylalumoxanes -
polymers with the elementary group of the formula

Card 1/2

Synthesis of New Polymers With Inorganic Chains of Molecules SOV/62-59-3-13/37

- Al - O - takes place. On the interaction of nonaethyl-
 $\begin{array}{c} | \\ \text{OSi}(\text{C}_2\text{H}_5)_3 \end{array}$
 alumoxy-trisiloxane with tris-triethyl-silylphosphate poly-
 organosilylphosphoralumoxanes with the elementary group of
 the formula



are formed. Similar polymers are also formed in the reaction
 of nonaethyl-alumoxy-trisiloxane with triethyl-silylphosphoric
 acid. There are 3 figures, 3 tables, and 5 Soviet references.

ASSOCIATION: Institut elementoorganicheskikh soyedineniy Akademii nauk SSSR
 (Institute of Elemental Organic Compounds of the Academy of
 Sciences, USSR)

SUBMITTED: June 25, 1957

Card 2/2

SOV/62-59-9-12/40

5(3)

AUTHORS:

Andrianov, K. A., Zhdanov, A. A.

TITLE:

Polyorgano-metallic Siloxanes. Communication 2. Synthesis of the Polyorgano-alumino-cobalt Siloxane and the Polyorgano-alumino Nickel Siloxane

PERIODICAL:

Izvestiya Akademii nauk SSSR. Otdeleniye khimicheskikh nauk, 1959, Nr 9, pp 1590-1594 (USSR)

ABSTRACT:


The present article describes the development of a method for the synthesis of the metallic silicon-organic polymers, which is based on the composition of the initial substances. The synthesis could be made according to the scheme $2\text{RSi}(\text{OH})_2\text{ONa} + \text{MeCl}_2 \rightarrow [\text{RSi}(\text{OH})_2\text{O}]_2\text{Me} + 2\text{NaCl}$ (1), at which attention has to be paid to the ratio $\text{CoCl}_2/\text{AlCl}_3$ in the reacting products in the case of aluminum - cobalt-organic compounds; here in addition to (1) the following secondary reactions occur:

$$\text{RSi}(\text{OH})_2\text{ONa} + \text{H}_2\text{O} \rightleftharpoons \text{RSi}(\text{OH})_3 + \text{NaOH} \quad (2), \quad \text{CoCl}_2 + 2\text{NaOH} \rightarrow$$

Card 1/2

SOV/62-59-9-12/40

Polyorgano-metallic Siloxanes. Communication 2. Synthesis of the Polyorgano-alumino-cobalt Siloxane and the Polyorgano-alumino Nickel Siloxane



$\rightarrow [\text{RSi(OH)}_2\text{O}]_3\text{Al} + 3\text{H}_2\text{O}$. Only if this ratio is below unity can Co satisfactorily enter the reaction. Figures 1 and 2 illustrate this dependence. The experimental part of the article describes the synthesis. Tables 1-3 list the analysis data of the products obtained. There are 2 figures, 3 tables, and 3 Soviet references.

ASSOCIATION: Institut elementoorganicheskikh sovedineniy Akademii nauk SSSR
(Institute of Element-organic Compounds of the Academy of Sciences, USSR)

SUBMITTED: January 3, 1958

Card 2/2

ZHDANOV, A.A., kand.khim,nauk

Scientific conference on silicon organic compounds, Vest.AN
SSSR 29 no.1:115-117 Ja '59. (MIRA 12:2)
(Silicon organic compounds)

5 (3)

AUTHORS:

Andrianov, K. A., Zhdanov, A. A.
Kazakova, A. A.

SOV/79-29-4-53/77

TITLE:

Synthesis of the Polymers With Inorganic Molecule Chains
(Sintez polimerov s neorganicheskimi tsepyami molekul).
I. Polyorganosiloxyposphoaluminumoxans (I. Poliorganosiloksifosforalyumoksany)

PERIODICAL:

Zhurnal obshchey khimii, 1959, Vol 29, Nr 4, pp 1281 - 1284
(USSR)

ABSTRACT:


In continuation of the preceding report (Ref 1) the investigations under review show that the polyalkylsiloxyaluminum phosphates are obtained by the polycondensation of the tris-(trialkylsiloxy)-aluminum with organo-phosphosilicon compounds according to schemes 1) and 2). The nature of the resulting polymers depends on the nature of the organic radical in the surrounding trialkylsiloxane groups. By the condensation of tris-(triethylsiloxy)-aluminum with triethylsiloxyphosphinic acid or tris-(triethylsilyl)-phosphate at 200-220° polymers were obtained which changed to an insoluble, not meltable, and solid state above the afore-mentioned temperature. Under the same conditions solid, not meltable, and insoluble products were

Card 1/3

Synthesis of the Polymers With Inorganic Molecule Chains. I. Polyorganosiloxyphosphoaluminumoxans

807/79-29-4-53/77

also obtained by the use of trimethylsiloxyphosphinic acid. In order to confirm the scheme mentioned 2 mols of tris-(triethylsiloxy)-aluminum were condensed with 1 mol of triethylsiloxyphosphinic acid. In this way the condensation product (III) of low molecular weight was obtained; hexaethylidisiloxane and water were eliminated in quantities corresponding to scheme 2. The analysis of the product corresponds to the formula given in scheme 2. By the same condensation, which was, in this case, carried out with equimolecular quantities, solid polymers of the composition



Powder, not meltable products which were, at the same time, insoluble in organic solutions resulted from the condensation of tris-(trimethylsiloxy)-aluminum with trimethylsiloxyphosphinic

Card 2/3

Synthesis of the Polymers With Inorganic Molecule
Chains. I. Polyorganosiloxyphosphoaluminumoxans

SOV/79-29-4-53/77

acid or with tris-(trimethylsilyl)-phosphate. There are 2
figures and 5 references, 4 of which are Soviet.

SUBMITTED: March 15, 1958

Card 3/3

5 (3)

AUTHORS:

Andrianov, K. A., Odinets, V. A.,
Zhdanov, A. A.,

SOV/79-29-5-21/75

TITLE:

On the Reaction of Acylation of Arylaliphatic Disiloxanes
(O reaktsii atsilirovaniya arilalifaticeskikh disiloksanov).
Synthesis of Bis-(4,4'-Acetobenzyl)-tetramethyl-disiloxane
(Sintez bis-(4,4'-atsetobenzil)-tetrametildisiloksana)

PERIODICAL:

Zhurnal obshchey khimii, 1959, Vol 29, Nr 5,
pp 1499-1503 (USSR)

ABSTRACT:

The authors concluded from the formation of benzyl methyl chloro-silanes and acylation of benzyl-trimethyl silane that the Friedel-Crafts reaction may be successfully applied to the synthesis of various benzyl siloxane derivatives in which the aromatic nucleus is separated from the silicon atom by the methylene group. Experiments indicated that benzyl-dimethyl-chloro-silane is not destroyed in the presence of aluminum chloride and can be used as initial product for the synthesis of bis-(acetobenzyl)-tetramethyl-disiloxane. The benzyl-dimethyl-chloro silane was prepared according to the Grignard reaction from dimethyl-dichloro-silane and benzyl magnesium chloride. The synthetic bis-(acetobenzyl)-tetramethyl-

Card 1/3

On the Reaction of Acylation of Arylaliphatic
Disiloxanes. Synthesis of Bis-(4,4'-Acetobenzyl)-tetramethyl-disiloxane

SOV/79-29-5-21/75

disiloxane has the properties of aliphatic-aromatic ketones and forms the dinitro-phenyl hydrazone in which case the reaction proceeds via both carbonyl groups. On oxidation of the bis-(acetobenzyl)-tetramethyl-disiloxane with sodium hypobromide in alkali the toluic acid is formed which was identified in the form of its methyl ester. A comparatively easy separation of the benzyl carboxy-group is connected with the displacement of the reactivity in the system of the conjugated nuclear bonds. In consequence of it a decrease of the electron density on the silicon nucleus and subsequent rupture of the Si-C-bond takes place under the influence of nucleophilic agents. When using alkaline potassium solution, the oxidation is complete and terephthalic acid is formed. The formation of the p-toluic and terephthalic acid indicates that the aceto-group comes into para-position with respect to the methylene group during the Friedel-Crafts reaction. Properties of the compounds synthesized are given in the table. There are 1 table and 6 references, 4 of which are Soviet.

Card 2/3

On the Reaction of Acylation of Arylaliphatic Disiloxanes. Synthesis of Bis-(4,4'-Acetobenzyl)-tetramethyl-disiloxane SOV/79-29-5-21/75

ASSOCIATION: Institut elementoorganicheskikh soedineniy Akademii nauk SSSR
(Institute of Elemental-Organic Compounds of the Academy of Sciences, USSR)

SUBMITTED: April 3, 1958

Card 3/3

5(3)

SOV/79-29-8-57/81

AUTHORS: Andrianov, K. A., Odinets, V. A., Zhdanov, A. A.

TITLE: On the Acylation Reaction of the Aryl Aliphatic Disiloxanes.
II. Synthesis of Silicon-organic Aromatic Ketones and Di-
functional Ketocarboxylic Acids

PERIODICAL: Zhurnal obshchey khimii, 1959, Vol 29, Nr 8,
pp 2702 - 2706 (USSR)

ABSTRACT: As the authors showed in a previous paper (Ref 1), benzyldi-
methylchlorosilane easily reacts with acetic anhydride in
the presence of $AlCl_3$, while bis-(4-acetobenzyl)-tetramethyl-
disiloxane is formed with a yield of 50%. In the present
paper this reaction was used in the synthesis of silicon di-
carboxylic acid and aromatic ketones. Benzyldimethylchloro-
silane and the acylating compounds (succinic acid - phthalic
anhydride and benzoylchloride) were used as a basis (Scheme 1).
By means of the reaction the best yield was achieved in a
benzene medium (50-60%). The acylation of benzyldimethyl-
chlorosilane with benzoylchloride leads to the aromatic di-
ketone according to scheme 2. Bis-(benzoylbenzyl)-tetramethyl-

Card 1/2

On the Acylation Reaction of the Aryl Aliphatic Disiloxanes. SOV/79-29-8-57/81
II. Synthesis of Silicon-organic Aromatic Ketones and Difunctional Keto-
carboxylic Acids

disiloxane was precipitated (40%). It forms easily the di-nitrophenylhydrazone which contains 11.44 % nitrogen, and thus indicates the presence of two ketone groups in the molecule of the synthesized compound. The molecular refraction of this siloxane was found to be 4 units higher than that of E. Warrick (Ref 6). (A. D. Petrov (Ref 5) found it to be higher by two units in 4-substituted silanes with one group). The data obtained show that the acylation of benzyldimethylchlorosilane is also possible with the anhydrides of the dicarboxylic acids and the acid chlorides of the monocarboxylic acids without a noticeable destruction of the compounds taking part in the reaction under the influence of hydrogen chloride. The properties of the compounds obtained are given in the table.

There are 1 table and 7 references, 4 of which are Soviet.

ASSOCIATION: Institut elementoorganicheskikh soyedineniy Akademii nauk SSSR
(Institute of Elemental-Organic Compounds of the Academy of
Sciences, USSR)

SUBMITTED: July 11, 1958
Card 2/2

SOV/80-32-2-52/56

AUTHORS: Andrianov, K.A., Zhdanov, A.A., Kashutina, E.A.

TITLE: Synthesis of Derived Molecular Di(triethylsiloxy)-Lead With Lead Hydroxide and Its Interaction With Titanium Tetrachloride (Sintez molekulyarnogo proizvodnogo di(trietilsiloksi)svintsa s gidrookis'yu svintsa i yego vzaimodeystviye s chetyrekh-khloristym titanom)

PERIODICAL: Zhurnal prikladnoy khimii, 1959, Vol XXXII, Nr 2, pp 463-464 (USSR)

ABSTRACT: During the development of new methods for the synthesis of trialkylsiloxymetals of the general formula (R_3SiO) a synthesis for tetra(triethylsiloxy)titanium from di(triethylsiloxy)-lead and titanium tetrachloride was found. The various steps of the experiment are described. There are 3 references, 2 of which are Soviet and 1 American.

SUBMITTED: April 24, 1958

Card 1/1

5 (2,3)
AUTHORS: Andrianov, K. A., Corresponding Member SOV/20-126-6-32/61
AS USSR, Zhdanov, A. A., Kashutina, E. A.

TITLE: Synthesis of Triethyl Siloxy Derivatives of Vanadium and Antimony (Sintez trietilsiloksi proizvodnykh vanadiya i sur'my)

PERIODICAL: Doklady Akademii nauk SSSR, 1959, Vol 126, Nr 6, pp 1261 - 1263 (USSR)

ABSTRACT: Among the syntheses for the production of compounds of type $(R_3SiO)_n Me$, where n denotes the valency of the metal, which are known at present, the interaction reaction of the trialkyl silanates of sodium and of some other metals is of special interest (see scheme). These monomers have an Si-O-Me bond and the synthesis of polymers which have alternating metal or oxygen atoms in the main chain is directly connected with their synthesis. By the method, illustrated by the above scheme, the authors synthesized for the first time the following compounds: a) tetrakis-(trimethyl-siloxy)-titanium (Ref 1); b) tetrakis-(dimethyl-phenyl-siloxy)-titanium (Ref 3); c) tetrakis-(triethyl-siloxy)-titanium (Ref 2), and d) tetrakis-(triethyl-siloxy)-tin (Ref 2). In the present paper the above mentioned

Card 1/3

Synthesis of Triethyl Siloxy Derivatives of Vanadium and Antimony SOV/20-126-6-32/67

method was further developed for the synthesis mentioned (see schemes). The experiments carried out produced yields of 60-70% of the theoretically possible yields. The lead-triethyl-silanolate (Ref 4) showed a considerable reactivity: by the action of I titanium-tetrachloride or of II vanadium oxychloride on its complex compound the following was formed: I Tetrakis-(triethyl-siloxy)-titanium or II tris-(triethyl-siloxy)-vanadate (see schemes). These reactions which were investigated by the authors with respect to the titanium-tetra- or vanadium-oxychloride, are of general importance for the production of trialkyl-silyl-derivatives of various elements. The investigations of the infra-red spectra of some of the compounds synthesized (by N. Gashnikova in the Vsesoyuznyy elektrotekhnicheskiy institut im. V. I. Lenina - All-Union Electrotechnical Institute imeni V. I. Lenin) proved the characteristic oscillation frequencies of $VO[OSi(C_2H_5)_3]_3$ which are mentioned in the paper.

Table 1 shows properties of the materials synthesized among others also of tris-(triethyl-siloxy)-stibine. There are 1 table and 4 Soviet references.

Card 2/3

Synthesis of Triethyl Siloxy Derivatives of Vanadium and Antimony SOV/20-126-6-32/67

ASSOCIATION: Institut elementoorganicheskikh soyedineniy Akademii nauk SSSR
(Institute of Elemental-organic Compounds of the Academy of Sciences, USSR)

SUBMITTED: April 10, 1959

Card 3/3

PHASE I BOOK EXPIRATION

SOV/1984

International symposium on macromolecular chemistry. Moscow, 1960.

Mezhdunarodnyy simpozium po makromolekulyarnoy khimii SSSR, Moskva, 14-18 Iyunya 1960 g.; doklady i avtorferaty. Sektora III Inzheneratsionnogo Svyaznogo na Makromolekularnuyu Khimiyu. Moscow, June 14-18, 1960; Papers and Summaries) Section III. [Moscow, Izd-vo AN SSSR, 1960] 469 p. 55,000 copies printed.

Tech. Ed.: P. S. Kashina.

Sponsoring Agency: The International Union of Pure and Applied Chemistry. Commission on Macromolecular Chemistry.

PURPOSE: This book is intended for chemists interested in polymerization reactions and the synthesis of high molecular compounds.

COVERAGE: This is Section III of a multivolume work containing papers on macromolecular chemistry. The articles in general deal with the kinetics of polymerization reactions, the synthesis of special-purpose polymers, e.g., ion exchange resins, semiconductor materials, etc., on exsolving polymerization reactions, properties, and chemical interactions of high molecular materials, and the effects of various factors on polymerization and the degradation of high molecular compounds. No personalities are mentioned. References given follow the articles.

Bar'ev, V. M., A. N. Privednikov, and S. S. Medvedev (USSR). The Effect of Formic Acid and Formates on the Oxidation of Hydrocarbons and Hydrocarbon Polymers 364

Kopceva, Z. V., and D. M. Znamenskiy (USSR). Study of the Effect of Some Organic and Organoelemental Compounds on the Thermal Degradation of Polyvinyl Chloride 372

Nichterie, O., E. Sittler, and P. Kefalin (Czechoslovakia). Degradation of Poly-f-Glycolactam as a Result of Exchange Reaction Between Amide Bonds 380

Swiders, M., J. Janikova, and E. Jralnick (Czechoslovakia). Neutralization of Residual Catalyst in Polydimethylsiloxane: Effect of Thermal Neutralization on the Thermal Stability of the Polymer 388

Omori, I., O. Kishinoh, and J. Simal (Czechoslovakia). Thermooxidative Degradation of Polyesters. Study of Degradation Reactions for Different Types of Linear Polyesters 405

Yezhuk, M. B., B. M. Komarova, L. I. Golubenkova, A. S. Kirilova, V. Lavrentyeva, and M. S. Kuzina (USSR). On the Degradation and Stabilization of Some Polymeric Materials 414

Spert, L. G., and A. S. Kurimansky (USSR). Investigation of the Efficiency of Additives of Rubber Oxidation at Various Temperatures 423

Pravdinov, A. M., and Ting Wen-K'ang (USSR). Mechanism of Lysis of Polystyrene 433

Zhdanov, A. V., and K. A. Medvedev (USSR). On the Hydrolytic Stability of Silyl Groups in Polymers With Inorganic Chains of Molecules 440

Berlin, A. A., Ye. A. Fenakova, and G. I. Volkova (USSR). Mechanicochemical Transformations and Block Copolymerization During the Freezing of Starch Solutions 444

Krasnov, Kh. N., B. I. Arhmedzhiev, and H. Asifov (USSR). Modification of the Properties of Cellulose by Grafting 447

5.3700(B)

5(3)

67941

SOV/20-130-1-20/69

AUTHORS: Andrianov, K. A., Corresponding Member AS USSR, Zhdanov, A. A.,
Odinets, V. A.

TITLE: Chloromethylation of Aryl-aliphatic Disiloxanes. Synthesis of
Chloromethylbenzyl dimethylchlorosilane and Its Derivatives

PERIODICAL: Doklady Akademii nauk SSSR, 1960, Vol 130, Nr 1, pp 75-78 (USSR)

ABSTRACT: The authors proved that the chloromethylation of the benzyl group bound to silicon can be successfully used for the synthesis mentioned in the subtitle (see Scheme). This reaction proceeds well in fuming hydrochloric acid. Paraform is used as an agent of chloromethylation. The chloromethylation in the presence of zinc chloride is accompanied by secondary processes. They form viscous, nondistillable products containing diphenyl-methane groups (see Scheme). The isolation of pure chloromethylbenzyl dimethylchlorosilane from the reaction mixture was attained by hydrolysis with excess water while the disiloxane mixture was split by strong sulfuric acid in the presence of ammonium chloride (see Scheme). The total yield in chloromethylbenzyl dimethylchlorosilane was 60% of the benzyl dimethylchlorosilane reacted, and 30% of the quantity used respectively. Direct fractionation of the chloromethylation products purified with water in the vacuum delivered smaller

Card 1/2

67947
SOV/20-130-1-20/69
Chloromethylation of Aryl-aliphatic Disiloxanes.
Synthesis of Chloromethylbenzyl-dimethylchlorosilane and Its Derivatives

yields. The end product obtained had all properties of the alkylchlorosilane halides. By hydrolysis with water, it readily forms the disiloxane. Bis-(chloromethylbenzyl)-tetramethyldisiloxane was isolated as a consequence of this reaction (see Scheme). By the action of potassium acetate on this latter substance in acetic medium, bis-(acetoxymethylbenzyl)-tetramethyldisiloxane was formed. On hydrolysis of the latter compound, the acetate group is split off. In the first stage, bis-(oxymethylbenzyl)-tetramethyldisiloxane develops which afterwards decomposes by the catalytic action of the alkali during distillation. Toluylmethanol and polydimethylsiloxanes with functional end groups as shown in the scheme are probably formed. Table 1 shows the properties of the substances synthesized. A. V. Topchiver and N. S. Nametkin are mentioned in the paper. There are 1 table and 8 references, 5 of which are Soviet.

SUBMITTED: September 30, 1959

Card 2/2

87861

S/191/60/000/005/007/020
B004/B064

15.8116

AUTHORS: Andrianov, K. A., Zhdanov, A. A., Baksheyeva, T. S.
TITLE: Synthesis of Organosilicon Oligomers Containing Oxyphenyl Groups
PERIODICAL: Plasticheskiye massy, 1960, No. 5, pp. 18 - 21

TEXT: Aim of the present study was the synthesis of organosilicon pol-

ymers with end groups of the following structure:
$$\begin{array}{c} \text{R} \\ | \\ -\text{O}-\text{Si}-\text{O}-\text{C}_6\text{H}_4-\text{C}(\text{CH}_3)_2-\text{C}_6\text{H}_4-\text{OH} \\ | \\ \text{R} \end{array}$$

Synthesis was carried out in two stages. First, organosilicon oligomers with butoxy end groups were produced. They were reacted with dihydroxydiphenyl propane. Phenyl-tributoxy silane, phenyl-methyl dibutoxy silane, and dimethyl-dibutoxy silane were the initial compounds used. They resulted from esterification of the respective chloro silanes. The oligomers with different degree of polymerization were produced by partial hydrolysis. Hydrolysis of 1 mole of dimethyl-dibutoxy silane with 0.5 moles

Card 1/3

87861

Synthesis of Organosilicon Oligomers
Containing Oxyphenyl Groups

S/191/60/000/005/007/020
B004/B064

of water yielded, in the presence of HCl, the dimer in a 73 % yield. 4 moles of dimethyl-dibutoxy silane yielded, with 3 moles of water, 41 % tetramer. 50 % hexamer was obtained from 6 moles of dimethyl-dibutoxy silane and 5 moles of water. Partial hydrolysis of 1 mole of phenyl-tributoxy silane with 1 mole of water gave an 86 % yield in polyphenyl-butoxy siloxane on heating in the presence of HCl. Phenyl-methyl dibutoxy silane was polymerized in the same way, but, in the presence of NaOH. The composition determined by equation $A = n/(n - m)$ was confirmed by elementary analysis (A = number of silicon atoms in the polymer chain, n = number of moles of the substance subjected to hydrolysis, m = number of moles of water used for hydrolysis). The oligomers with butoxy end groups were reacted, in the presence of Na- or Al butylate, with dihydroxydiphenyl propane. The ratio of components was 1:1. 1-n-butoxy-polydimethyl siloxane yielded a polymer with the degree of polymerization 246; 1-n-butoxy-polyphenyl-methyl siloxane gave a polymer whose degree of polymerization was 2468. Determination of the butanol set free during the reaction showed that the reaction proceeds up to a yield of 80 %. The resulting organosilicon compounds which contained the end group

Card 2/3

87881

Synthesis of Organosilicon Oligomers
Containing Oxyphenyl Groups

S/191/60/000/005/007/020
B004/B064

$\text{SiOC}_6\text{H}_4\text{C}(\text{CH}_3)_2\text{C}_6\text{H}_4\text{OH}$ were highly reactive to aldehydes. Urotrepine or furfurole caused rapid polymerization under the formation of insoluble, non-melting, three-dimensional polymers. There are 3 tables and 3 references: 2 Soviet and 1 US.

X

Card 3/3

S/190/60/002/007/011/017
B020/B052

AUTHORS: Andrianov, K. A., Zhdanov, A. A.

TITLE: Investigation of the Polymerization of Polyorganosiloxanes
Under the Influence of Polyaluminum Ethyl Siloxanes

PERIODICAL: Vysokomolekulyarnyye soyedineniya, 1960, Vol. 2, No. 7,
pp. 1071-1076

TEXT: The authors found that polyaluminum organosiloxanes reduce the reaction time of the polymerization of polyorganosiloxanes obtained from trifunctional, and bi- and trifunctional monomers. The reaction time of the polyorganosiloxane polymerization in dependence on the amount of the polyaluminum organosiloxane introduced, was investigated to explain the rules governing the above polymerization. Polymers produced by cohydrolysis of methylchloro silane and phenyl trichloro silane, methyl triacetoxy silane, and phenyl acetoxy silane (polymer 1-A) were used for this investigation. Polyaluminum siloxane A-16 (Ref. 1) was used as catalyst. Table 1 gives the characteristics of the polymers used. Fig. 1 shows the dependence of the polymerization time on the amount of the

Card 1/3

Investigation of the Polymerization of Poly-
organosiloxanes Under the Influence of
Polyaluminum Ethyl Siloxanes

S/190/60/002/007/011/017
B020/B052

added polymer A-16. Already with 0.5% of the polymer A-16, a considerable reduction of the polymerization time was found. Fig. 2 shows the dependence of the polymerization time of a 99% mixture of 1-X (1-Kh) and 1% of A-16 on the amount of dimethyl aniline and pyridine, respectively. The amount of the tertiary amine addition also reduces the polymerization time of the polymers 1-Kh and 1-A (Figs. 4,5). For the evaluation of the maxima of the curves shown in Figs. 2 and 3, the molar ratio between tertiary amine and aluminum in the mixtures investigated, was calculated for points corresponding to the maximum value of the polymerization time (Table 2). The maximum polymerization time in all cases approximately corresponds to the equimolar ratio between the amount of the amine addition and the aluminum in the polymer molecule. The mechanism of the interaction between polyaluminum ethyl siloxane and the organosilicon polymer was explained by the data obtained. Finally, the syntheses of polymers 1-Kh, 1-A, and A-16 are described. Their elementary composition is given in Table 1. The determination of the polymerization time is also described, respective results being graphically presented in Figs. 1 to 5. There are 5 figures, 2 tables, and 1 Soviet reference.


Card 2/3

Investigation of the Polymerization of Poly-
organosiloxanes Under the Influence of
Polyaluminum Ethyl Siloxanes

S/190/60/002/007/011/017
B020/B052

ASSOCIATION: Institut elementoorganicheskikh sovedineniy AN SSSR
(Institute of Elemental-organic Compounds of the AS USSR)

SUBMITTED: March 16, 1960



Card 3/3

ANDRIANOV, K.A.; ZHDANOV, A.A.

Process of the polymerization of polyorganosiloxanes, induced by
polyaluminioethyl siloxanes. Vysokom.soed. 2 no.7:1071-1076
Jl '60. (MIRA 13:8)

1. Institut elementoorganicheskikh sovedineniy AN SSSR.
(Polymerization) (Siloxanes)

S/661/61/000/006/051/081
D235/D302

AUTHORS: Zhdanov, A. A. and Andrianov, K. A.

TITLE: Polyorgano-metallo-siloxanes and polyorgano-siloxy-metalloxanes

SOURCE: Khimiy i prakticheskoye primeneniye kremneorganicheskikh soyedineniy; trudy konferentsii, no. 6: Doklady, diskussii, resheniye. II Vses. konfer. po khimii i prakt. prim. kremneorg. soyed., Len. 1958. Leningrad, Izd-vo AN SSSR, 1961, 220-224

TEXT: A discussion of the above paper (this publication, no. 2, p. 100) between the authors and N. F. Orlov (IKhS AN SSSR, Leningrad), S. N. Borisov, (VNIISK, Leningrad) and M. G. Voronkov (IKhS AN SSSR, Leningrad). The following points are discussed: Thermal and hydrolytic stability of the bonds silicon-oxygen-metal; introduction of the elements magnesium and zinc into the siloxane structure; the formation of poly-diethyl-alumina-siloxane; reasons for the increase in thermal stability obtained by the authors; thermal

Card 1/3

Polyorgano-metallo-siloxanes ...

S/661/61/000/006/051/081
D235/D302

and hydrolytic stability of poly-organo-titanium siloxanes. The thermal stability of the bonds Si-O-M is fairly high and a compound such as $(R_2SiO)_2Ti$ is hydrolyzed only very slowly by water. Magnesium reacts like aluminum with hydroxyl containing silicon compounds to give hydrogen and the siloxane polymer containing magnesium. Reference is made to a patent by Viberg and Katnslev where poly-diethyl-alumina-siloxane is obtained by reacting the metal with diethyl siloxane at $310^\circ C$; the authors only obtained a 1.5 - 2% yield by such a reaction. Alkaline hydrolysis of dimethyl-siloxane with aluminum chloride in the ratio Si-Al of 3:1 to 45:1 leads to the formation of gel-like polymers and in the ratio Si:Al of 60:1 to 100:1 to co-polymers similar to poly-dimethyl-siloxane rubbers, but the exterior is frequently gummy. Thermal stability of poly-organo-titanium-siloxanes is considerably higher than for the aluminum compounds. The bond Si-O-Ti has higher thermal stability than the compounds with a siloxane bond due to the effect of oxygen on Si-C under the action of titanium. The hydrolytic stability depends on the nature of the radical connected to silicon and the molecular structure. Derivatives from elements of group V possess the greatest

Card 2/3

Polyorgano-metallo-siloxanes ...

S/661/61/000/006/051/031
D235/D302

stability, as compared with derivatives from groups III and IV, but there is no quantitative information concerning this.

ASSOCIATION: Institut elementoorganicheskikh soedineniy Akademii nauk SSSR, Moskva (Institute of Elemental Organic Compounds, Academy of Sciences, USSR, Moscow)

Card 3/3

✓

69484

15.8114

2209


S/079/61/031/001/018/025
B001/B066

AUTHORS: Andrianov, K. A., Zhdanov, A. A., Khanarashvili, L. M., and Shapatin, A. S.

TITLE: Reactions of Aluminum Isopropylate With Some Organo-phosphorus Compounds.

PERIODICAL: Zhurnal obshchey khimii, 1961, Vol. 31, No. 1, pp. 224 - 228

TEXT: The authors studied the reaction of aluminum isopropylate with the acid chlorides of methyl-m-cresoxy phosphinic acid and dimethyl phosphinic acid, in order to use them as initial products for the synthesis of polymers with inorganic molecular chains. One of the initial organo-phosphorus compounds, the acid chloride of methyl-m-cresoxy phosphinic acid, was obtained by reaction of methyl phosphinic acid dichloride with m-cresol at 120 - 140°C:




Card 1/3

Reactions of Aluminum Isopropylate With Some Organophosphorus Compounds

88484

S/079/61/031/001/018/025
B001/B066

As by-product, considerable quantities of di-m-cresyl ester of methyl phosphinic acid are formed. Higher excess of the dichloride of methyl phosphinic acid gives a large yield of the chloride of methyl-m-cresoxy phosphinic acid and a low yield of the afore-mentioned by-product. The reaction of the chloride of methyl-m-cresoxy-phosphinic acid with aluminum isopropylate was expected to proceed according to the following equation:




However, in addition to isopropyl chloride, also the isopropyl-m-cresyl ester was separated which is indicative of side reactions. At an elevated reaction temperature (140 - 200°C) still more complicated compounds resulted, which renders the separation of individual reaction products very difficult. To confirm the assumption on the course of reaction, tris(methyl-m-cresoxy-phosphinoxy)aluminum was synthesized. The reaction was carried out at 90 - 100°C to avoid separation of the cresoxy group. Under these conditions, tris(methyl-m-cresoxy-phosphinoxy)aluminum resulted in a yield of 59 %, isopropylchloride in a yield of 67 %, which Card 2/3

Reactions of Aluminum Isopropylate With Some
Organophosphorus Compounds

88484

S/079/61/031/001/018/025
B001/B066

confirmed the predicted course of reaction. The reaction of dimethyl phosphinic acid with aluminum isopropylate takes place according to equation (5):



This is confirmed by a nearly quantitative separation of isopropyl alcohol (99 %). According to ultimate analysis, the product distilling from the reaction mass at 164°C corresponds to dimethyl-phosphinoxy-(diisopropyl) aluminum which is contaminated. The vitreous, colorless product is soluble in common aromatic solvents. G. B. Ravich and I. F. Manucharova are thanked for their cooperation. There are 1 figure and 10 references: 4 Soviet, 2 British, 2 German, and 1 Czechoslovakian.

ASSOCIATION: Moskovskiy institut tonkoy khimicheskoy tekhnologii
(Moscow Institute of Fine Chemical Technology)

SUBMITTED: February 20, 1960

Card 3/3

31193

S/079/61/031/012/007/011
D258/D301

S.3700

AUTHORS: Andrianov, K. A., Zhdanov, A.A., and Odinets, V. A.
TITLE: The addition of aromatic derivatives to vinyl methyl dichlorosilane
PERIODICAL: Zhurnal obshchey khimii, v. 31, no. 12, 1961, 4033-4038

TEXT: The authors showed that the addition of either benzene, toluene, chlorobenzene or diphenyl to vinyl methyl dichlorosilane yields the corresponding (β -aryl ethyl)-methyldichlorosilanes and also a higher boiling by-product: $\text{ArH} + \text{CH}_2 = \text{CHSi}(\text{CH}_3)\text{Cl}_2 - \text{AlCl}_3$


\longrightarrow $\text{ArCH}_2\text{CH}_2\text{Si}(\text{CH}_3)\text{Cl}_2 \dots (1)$. The by-product was isolated in the case of benzene and identified as bis-(2-dichloromethyl silyl ethyl)-benzene, formed on further reaction of the primary product with a second molecule of the silane:

Card 1/3

31193

S/079/61/031/012/007/011
D258/D301

The addition of aromatic ...



The primary addition products were converted to the corresponding silane diols by acetylation with CH_3COOK and subsequent hydrolysis.

The infrared-spectra of all these diols confirm the presence of Si-CH_3 groups (1258 cm^{-1}), of an aromatic nucleus and of SiOH groups ($830 - 880 \text{ cm}^{-1}$). The authors conclude that the phenyl compound adds on in the β -position (with respect to Si). The syntheses of the primary addition products are then described: The melting points of the benzene, toluene, chlorobenzene, and diphenyl derivatives were 80-81, 70, 89-91, and 132-134°C respectively. There are 4 figures, 1 table and 3 references: 1 Soviet-bloc and 2 non-Soviet-bloc. The references to the English-language publications read as follows: G. H. Wagner, D. L. Bailey, A. H.

Card 2/3

31193

S/079/61/031/012/007/011
D258/D301

The addition of aromatic ...

Pines, M. L. Dunham, Ind. Eng. Ch., no. 2, 368, (1953); R. E. Richard, H. W. Thompson, J. Chem. Soc., (1949), 124.

SUBMITTED: November 29, 1960

X

Card 3/3

15,8170

37775

S/661/61/000/006/068/081
D247/D302

AUTHORS: Konstantinova, N. G., Zhdanov, A. A., Andrianov, K. A.,
Sharov, M. Ya., Kyutner, M. A. and Zakharov, A. A.

TITLE: Thermostable lacquer coatings based on silico-organic
polymers

SOURCE: Khimiya i prakticheskoye primeneniye kremneorganiches-
kikh soyedineniy; trudy konferentsii, no. 6: Doklady,
diskussii, resheniye. II Vses. konfer. po khimii i
prakt. prim. kremneorg. soyed., Len. 1958. Leningrad,
Izd-vo AN SSSR, 1961, 296-299

TEXT: A study was made of the thermostability of several lacquer-
painted materials on the basis of different film-forming substan-
ces. The silico-organic resin K-47 was modified by the use of orga-
nic polymers to give a hard, cold-drying coat of increased thermo-
stability. The metallic surface and its preparation was found to
have a great influence on the adhesion, the protective properties
and the thermostability of the coatings. In the discussion, the

X

Card 1/2

Thermostable lacquer coatings ...

S/661/61/000/006/068/081
D247/D302

registration and technical specifications of some of the silico-organic varnishes are given. Elasticity and hardness data are also given. Coatings withstanding radioactive irradiation are mentioned. Comparison of the properties of silico-organic and other enamels are made, and methods of preparing surfaces before application of the enamels are mentioned. The best thermostability recorded was for a duration of 150 hours at 500°C. A discussion followed in which P. A. Filippov (Leningrad) took part.

X

Card 2/2

23837

15. 8114 2209

S/020/61/138/002/020/024
B103/B220

AUTHORS: Andrianov, K. A., Corresponding Member AS USSR, and Zhdanov, A. A.

TITLE: Polycondensation as a method of producing polydialkyl siloxane and polyaluminum dialkyl siloxane elastomers

PERIODICAL: Akademiya nauk SSSR. Doklady, v. 138, no. 2, 1961, 361-362

TEXT: A new method of synthesizing polydialkyl siloxane elastomers having straight molecular chains is discussed. It is based on the polycondensation of bi-functional oligomers with bi-functional silicoorganic monomers. This process takes place in 2 stages: 1) production of oligomers by the known methods (see diagram no. 1); 2) polycondensation or heterofunctional polycondensation of the monomers produced, whereby elastomers of high molecular weight are formed. Of the elastomers having inorganic principal chains and framing organic radicals only polydimethyl siloxane elastomers including modifications are known. Up to the present, it has not been possible to produce elastomers by hydrolysis and polycondensation or by heterofunctional polycondensation of different bi-functional monomers; the

Card 1/6

23837

Polycondensation as a method of producing... 8/020/61/138/002/020/024
B103/B220

side reactions caused the formation of linear as well as cyclic products. The characteristic of the method described by the authors is based on the fact that in the two-stage process mentioned the formation of cycles of low molecular weight in the final stage is impossible. The oligomers subject to polycondensation have such a degree of polymerization that ring formation becomes impossible. From elastomers produced by this method, types of rubber can be produced by vulcanization, which have properties analogous to those of standard polydimethyl siloxane rubber. Furthermore, the authors stated that differently high polycondensated α, ω -dihydroxy polydimethyl siloxanes undergo the following reactions, whereby linear polymers are formed with atoms of aluminum, titanium, or boron in the inorganic polymer chain: aluminum butylate gives $[(CH_3)_2SiO]_{28}[Al(OC_4H_9)O]$ with a molecular weight of 30000; tributoxy boron gives $[(CH_3)_2SiO]_{35}[B(OC_4H_9)O]$, molecular weight 34000; tetrabutoxy titanate gives $[(CH_3)_2SiO]_{35}[Ti(OC_4H_9)O]$. Dependent on the functional end groups of the oligomers, the polycondensation can proceed with formation of various products of low molecular weight (see diagram no. 2). The

Card 2/6

Polycondensation as a method of producing...

S/020/2387
617-138/002/020/024
B103/B220

polymers produced by the authors are elastic soluble substances with a molecular weight of 100000 to 200000. Those having a metal atom in the chain are highly reactive due to the retaining of the functional group at the metal atom. The rubber materials, thus obtained, are similar to those produced from polydimethyl siloxanes, but have still better properties. α,ω -dichloro polydimethyl siloxanes were produced by the abovementioned methods: K. A. Andrianov, V. V. Severnyy, B. G. Zavin (Ref. 4: Izv. AN SSSR, OKhN, being printed): $\text{Cl}[(\text{CH}_3)_2\text{SiO}]_{41}\text{Si}(\text{CH}_3)_2\text{Cl}$.

Therefrom, oligomers were produced with siloxane chains of various lengths from which α,ω -dihydro polydimethyl siloxanes were obtained by hydrolysis. These siloxanes were produced equally from dimethyl diacetoxy siloxane. Mention is made of white soot Y-333 40 (U-333 40) and of the method of determining the molecular weights by Terent'yev, which is, however, not explained in detail. The polymer $[(\text{C}_6\text{H}_5)(\text{CH}_3)\text{SiOAl}(\text{OC}_4\text{H}_9)\text{O}]_n$ was

produced from phenylmethyl diacetoxy silane with aluminum butylate. There are 1 table and 5 references: 3 Soviet-bloc and 2 non-Soviet-bloc. The two references to English-language publications read as follows: Ref. 2: J. F. Hyde, J. Am. Chem. Soc., 75, 2166 (1953); Ref. 3: T. Takiguchi, X

Card 3/6

23837

Polycondensation as a method of producing...

S/020/61/138/002/020/024
B103/B220

Bull. Chem. Soc. Japan, 32, 556 (1959).

ASSOCIATION: Institut elementoorganicheskikh sovedineniy Akademii nauk
SSSR (Institute of Elemental-organic Compounds, Academy of
Sciences USSR)

SUBMITTED: February 6, 1961

Card 4/6

152170

25214

S/062/61/000/007/004/009
B117/B215

AUTHOR: Zhdanov, A. A., Andrianov, K. A., and Bogdanova, A. A.

TITLE: Reaction of aluminum chloride with dialkyl cyclosiloxanes

PERIODICAL: Akademiya nauk SSSR. Izvestiya. Otdeleniye khimicheskikh nauk, no. 7, 1961, 1261 - 1266

TEXT: The interaction of aluminum chloride with dimethyl- and diethyl cyclosiloxanes was investigated in a study of the methods of producing polyalumo-organosiloxanes. A flask with mixer, thermometer, re cooler, and cooling vessels for collecting the reaction products were used for the experiments. It was found that aluminum chloride reacts easily with dimethyl- and diethyl cyclosiloxanes at equimolecular ratios. Crystalline reaction products are formed which are quantitatively sublimated in vacuo. In the examination of the reaction mixture obtained by reaction between octamethyl cyclotetrasiloxane and aluminum chloride (mixing time: 10 hr at 120°C), the following reaction products were isolated: 1,3-dichloro tetramethyl disiloxane, boiling point: 32° - 36°C (10 mm); 1,5-dichloro hexamethyl trisiloxane, boiling point: 72° - 75°C (10 mm); 1,7-dichloro octamethyl tetrasiloxane, boiling point: 90° - 95°C (10 mm); a

Card 1/4


X

25214


S/062/61/000/007/0C4/009
B117/B215

Reaction of aluminum chloride ...

crystalline substance, boiling point: 152° - 153°C, of the empirical composition $C_8H_{24}O_6Cl_5Si_4Al_3$. The formation of these products in the reaction mixture followed the scheme



The crystalline substance of the above empirical formula showed a constant composition in repeated sublimation. On the basis of analytical data and chemical studies it may be assumed that the respective substance contains a complex aluminum chloride molecule. The reaction between aluminum chloride and hexamethyl cyclotrisiloxane (mixing time: 6 hr at 50° - 60°C) is similar to the previous one, with the only difference that besides the crystalline substance also dimethyl dichlorosilane and highest α, ω -dichloro polysiloxanes are formed. This process may be expressed by the scheme



Similar ethyl derivatives were isolated in the reaction between aluminum chloride and octaethyl cyclotetrasiloxane (mixing time: 11 hr at 120°C)

Card 2/4

25214

Reaction of aluminum chloride ...

S/062/61/000/007/004/009
B117/B215

1,3-dichloro tetraethyl disiloxane, boiling point: $85^{\circ} - 90^{\circ}\text{C}$ (10 mm);
1,5 dichlorohexaethyl trisiloxane, boiling point: $124^{\circ} - 131^{\circ}\text{C}$ (10 mm);
1,4-dichloro octaethyl tetrasiloxane, boiling point: $131^{\circ}\text{C} - 145^{\circ}\text{C}$
(10 mm); a crystalline substance which is sublimated at $225^{\circ}\text{C} - 233^{\circ}\text{C}$,
melting point: 112°C (unstable), of the empirical composition
 $\text{C}_{16}\text{H}_{40}\text{O}_6\text{Cl}_2\text{Si}_4\text{Al}_3$. The structures of the crystalline substances are
similar in both cases. An identical, crystalline substance of the
above composition and highest polydiethyl siloxanes were obtained in
the reaction between aluminum chloride and hexaethyl cyclotrisiloxane
(mixing time: 5 hr at 80°C). Conclusion: Rupture of the cycle takes
place in the interaction of aluminum chloride and the above cyclic
dialkyl siloxanes, and α -chloro- ω -dichloro alumoxydialkyl polysilox-
anes are formed. The latter then separate α, ω -dichloro polysiloxanes
and form cyclic compounds: 1-chloro-3,3,5,5-tetramethyl cycloalumo-
disiloxane and 1-chloro-3,3,5,5-tetraethyl cycloalumodisiloxane.
These compounds were isolated and characterized in the form of com-
plexes with aluminum chloride. There is 1 non-Soviet-bloc reference.

Card 3/4

25214
Reaction of aluminum chloride ...

S/062/61/000/007/004/009
B117/B215

ASSOCIATION: Institut elementoorganicheskikh sovedineniy Adademii nauk
SSSR (Institute of Elemental Organic Compounds of the
Academy of Sciences USSR)

SUBMITTED: September 26, 1960

Card 4/4

KORSHAK, V.V.; VINOGRADOVA, S.V.; FRUNZE, T.M.; GRIBOVA, I.A.;
ZHDANOV, A.A.; MOZGOVA, K.K.; KRONGAUZ, Ye.S., red.izd-va;
TIKHOMIROVA, S.G., tekhn.red.

[Chemistry and technology of synthetic macromolecular compounds.
Heterocyclic compounds]. Khimiia i tekhnologiya sinteticheskikh
vysokomolekuliarnykh soedinenii. Geterotsepnnye soedinenia:
Moskva, Izd-vo Akad.nauk SSSR. 1961. 721 p. (Itogi nauki:
Khimicheskie nauki, no.7) (MIRA 14:11)

1. Chlen-korrespondent AN SSSR (for Korshak).
(Macromolecular compounds)
(Heterocyclic compounds)

15.8170

27491
S/062/61/000/009/006/014
B117/B101AUTHORS: Andrianov, K. A., Zhdanov, A. A., and Odinets, V. A.

TITLE: Synthesis of liquid 1,n-hexamethyl-poly(phenyl-ethyl)-methyl siloxanes and investigation of their properties

PERIODICAL: Akademiya nauk SSSR. Izvestiya. Otdeleniye khimicheskikh nauk, no. 9, 1961, 1615-1624.

TEXT: The lowest-molecular members of the polymerhomologous series of 1,n-hexamethyl-poly(phenyl-ethyl)-methyl siloxanes were synthesized and their properties studied. The work was undertaken to study the dependence of the polar properties of these liquid organo-silicon polymers on various polar substituents at the benzene ring. The polar properties were studied on the basis of the activation energy of viscous flow and the temperature dependence of the viscosity. The flowing initial substances were used for the synthesis: (phenyl-ethyl)-methyl-dichloro silane ($C_6H_5C_2H_4(CH_3)SiCl_2$, b.p. $90^{\circ}-92^{\circ}C$ (5 mm Hg)), (tolyl-ethyl)-methyl-dichloro silane ($CH_3C_6H_4C_2H_4(CH_3)SiCl_2$, b.p. $103^{\circ}-105^{\circ}C$ (2 mm Hg)), (chloro-

X

Card 1/6

27491

S/062/61/000/009/006/014
B117/B101

Synthesis of liquid 1,n-hexamethyl- ...

phenyl-ethyl)-methyl-dichloro silane ($\text{ClC}_6\text{H}_4\text{C}_2\text{H}_4(\text{CH}_3)\text{SiCl}_2$, b.p. 124°-126°C (2 mm Hg). The synthesis of these compounds is described in Ref. 11 (K. A. Andrianov, et al. Zh. obshch. khimii (in print)). The liquid polymers were obtained by the joint hydrolysis of toluene solution of mixtures of these compounds with trimethyl-chloro silane (b.p. 58°-59°C) at 90-95°C. Polymers of varying degrees of polymerization, according to the reactant ratio, may be isolated from the reaction mixture (Table 1). Hydrolysis of ethereal solution of (phenyl)-methyl-dichloro silane yielded cyclic polymers also: tri(phenyl-ethyl)-trimethyl cyclotrisiloxane $[\text{C}_6\text{H}_5\text{C}_2\text{H}_4(\text{CH}_3)\text{SiO}]_3$ and tetra(phenyl-ethyl)-tetramethyl cyclotetrasiloxane $[\text{C}_6\text{H}_5\text{C}_2\text{H}_4(\text{CH}_3)\text{SiO}]_4$. Evaluation of the infrared spectra of the compounds investigated indicates that the addition of the vinyl aromatic nucleus takes place in β position, giving β -substituted derivatives. The density of the liquids was determined pycnometrically. Viscosity measurements were carried out by standard methods with an Ostwald-Pinkevich viscosimeter. Data on the activation energy of viscous flow and the temperature coefficients of the viscosity are shown in Table 2. It was found that for the lowest-molecular members of the homologous series the

Card 2/6

27491

S/062/61/000/009/006/014
B117/B101

Synthesis of liquid 1,n-hexamethyl- ...

activation energy of viscous flow is hardly dependent on the polar groups. Substitution of the hydrogen atom at the nucleus by methyl or chlorine, however, always increases the activation energy. The activation energy of flow depends on the number of silicon atoms in the polymers under study. The polar properties of the radicals investigated decreases in the order $-\text{C}_2\text{H}_4\text{C}_6\text{H}_4\text{Cl} > -\text{C}_2\text{H}_4\text{C}_6\text{H}_4\text{CH}_3 > -\text{C}_2\text{H}_4\text{C}_6\text{H}_5$. There are 12 figures, 2 tables, and 12 references: 7 Soviet and 5 non-Soviet. The three references to English-language publications read as follows: C. C. Currie, *Industr. and Engng. Chem.* 46, 2331 (1954); L. H. Sommer, R. P. Pioch, *J. Amer. Chem. Soc.* 75, 6337 (1953); L. H. Sommer, W. D. English, G. R. Ansul, D. N. Vivona, *J. Amer. Chem. Soc.* 77, 2485 (1955).

ASSOCIATION: Institut elementoorganicheskikh soedineniy Akademii nauk SSSR (Institute of Elemental Organic Compounds of the Academy of Sciences USSR)

SUBMITTED: December 12, 1960

Card 3/6

ANDRIANOV, K.A.; ZHDANOV, A.A.; ODINETS, V.A.

Reaction of addition of aromatic derivatives to vinylmethyldichlorosilane.
Zhur.ob.khim. 31 no.12:4033-4038 D '61. (MIRA 15:2)
(Aromatic compounds)
(Silane)

ANDRIANOV, K.A.; ZHDANOV, A.A.; KASHUTINA, E.A.

Reaction of diethylmethoxychlorosilane with sodium derivatives of acetylacetonate and acetoacetic ester. Zhur. ob. khim. 32 no.1:297-301 Ja '62. (MIRA 15:2)

(Silane) (Pentanedione) (Acetoacetic acid)

ANDRIANOV, Kuz'ma Andrianovich; KORSHAK, V.V., otv. red.; ZHDANOV,
A.A., red.; BALLOD, A.I., tekh. red.; DOROKHINA, I.N., tekh.
red.

[Polymers with inorganic main chains of molecules] Polimery s
neorganicheskimi glavnyimi tsepiami molekul. Moskva, Izd-vo
Akad. nauk SSSR, 1962. 326 p. (MIRA 16:2)

1. Chlen-korrespondent Akademii nauk SSSR (for Korshak).
(Silicon organic compounds) (Polymers)
(Organometallic compounds)

ANDRIANOV, K.A.; ZHDANOV, A.A.; KASHUTINA, E.A.

Synthesis of polyorganosiloxane oligomers containing malonate end groups. Izv.AN SSSR.Otd.khim.nauk no.3:454-456 Mr '62.

(MIRA 15:3)

1. Institut elementoorganicheskikh soyedineniy AN SSSR.
(Silicon organic compounds) (Malonic acid)

35592
S/062/62/000/003/008/014
B117/B144

15.8170

AUTHORS: Andrianov, K. A., Zhdanov, A. A., and Kashutina, E. A.

TITLE: Synthesis of polyorganosiloxane-oligomers with terminal malonate groups

PERIODICAL: . Akademiya nauk SSSR. Izvestiya. Otdeleniye khimicheskikh nauk, no. 3, 1962, 454-456

TEXT: The joint hydrolysis of dimethyl-diethoxy silane and (diethyl-malonylmethyl)dimethyl-ethoxy silane was studied. Dimethylchloromethyl-ethoxy silane synthesized by the method described by K. A. Andrianov and M. A. Golubenko (Ref. 4: Dokl. AN SSSR 112, 257 (1957)), boiling point 131-133°C, dimethyl-diethoxy silane, boiling point 112-116°C and freshly distilled malonic ester were used. The reaction was shown to take a smooth course in slightly acid medium without cleavage of ethoxy groups in malonic ester rests. Polyorganosiloxane-oligomers with terminal malonate groups are formed here. Investigation of infrared spectra of the compounds produced showed that the malonic ester residue is not added to the oxygen atom, but to the carbon atom. The following compounds were synthesized:

Card 1/3

S/062/62/000/003/008/014

B117/B144

Synthesis of polyorganosiloxane-oligomers...

(diethylmalonylmethyl) dimethylethoxysilane, $C_{10}H_{19}O_4Si$, yield 42 %, clear, colorless liquid, boiling point 120-123°C (5 mm Hg), n_D^{20} 1.4312, d_4^{20} 1.0058, MR 71.29; 1,3-bis-(diethylmalonylmethyl)tetramethylsiloxane, $C_{20}H_{38}O_9Si_2$, yield 78.4 %, clear, colorless liquid, boiling point 184-188°C (2 mm Hg), n_D^{20} 1.4425, d_4^{20} 1.0588, MR 119.94; 1,5-bis-(diethylmalonylmethyl) hexamethyltrisiloxane, $C_{22}H_{44}O_{10}Si_3$, heavy, colorless liquid, boiling point 232-234°C (7-8 mm Hg), n_D^{20} 1.4363, d_4^{20} 1.0425, MR 138.93; 1,7-bis-(diethylmalonylmethyl) octamethyltetrasiloxane, $C_{24}H_{50}O_{11}Si_4$, clear, colorless liquid, boiling point 242-255°C (8-10 mm Hg), n_D^{20} 1.4338, d_4^{20} 1.0375, MR 157.56; 1,17-bis-(diethylmalonylmethyl) octadecamethylnonasiloxane, $C_{34}H_{80}O_{16}Si_9$, n_D^{20} 1.4250, d_4^{20} 1.0190, MR 250.66; 1,37-bis-(diethylmalonylmethyl) octatricosamethylnonadecasiloxane, $C_{54}H_{140}O_{26}Si_{19}$, clear, viscous liquid, n_D^{20} 1.4165, d_4^{20} 1.0068, MR 434.48. N. S. Leznov and

Card 2/3

Synthesis of polyorganosiloxane-oligomers...

S/062/62/000/003/008/014
B117/B144

Ya. I. Mindlin are mentioned. There are 2 figures and 4 references:
2 Soviet and 2 non-Soviet. The references to English-language publications
read as follows: L. Sommer, G. Goldberg, G. Barnes, L. Stone, J. Amer.
Chem. Soc. 76, 1609 (1954); L. Sommer, J. Masterson, O. Steward,
R. Leitheiser, J. Amer. Chem. Soc. 78, 2010 (1956).

ASSOCIATION: Institut elementoorganicheskikh soyedineniy Akademii nauk
SSSR (Institute of Elemental Organic Compounds of the
Academy of Sciences USSR)

SUBMITTED: September 26, 1961

Card 3/3

36635
S/062/62/000/004/004/013
B110/B101

15.9205

AUTHORS: Andrianov, K. A., and Zhdanov, A. A.

TITLE: Polyboron dimethyl siloxanes

PERIODICAL: Akademiya nauk SSSR. Izvestiya. Otdeleniye
khimicheskikh nauk, no. 4, 1962, 615-619


TEXT: Polyboron dimethyl siloxanes, which are of interest as elastomers (molecular weight 200,000-400,000), were produced by heterofunctional polycondensation as described by the authors (Dokl. AN SSSR 138, 361 (1961)). In the first stage, 326 g (1.1 moles) of octamethyl cyclotetrasiloxane was telomerized in the presence of 2.37 g (0.0184 moles) of dimethyl dichlorosilane in an autoclave for 4 hrs at 200°C. The resultant substance, 79 g of colorless, viscous α,ω -dichloro polydimethyl siloxane $(\text{ClSi}(\text{CH}_3)_2\text{O}[\text{Si}(\text{CH}_3)_2\text{O}]_n\text{Si}(\text{CH}_3)_2\text{Cl})$ was hydrolyzed in acetone and benzene by means of sodium bicarbonate, whereby 72 g of colorless, viscous α,ω -dioxo polydimethyl siloxane, $[(\text{CH}_3)_2\text{SiO}]_m$, was obtained. The molecular weight of the compound was calculated from

Card 1/4

S/062/62/000/004/004/013
B110/B101

Polyboron dimethyl siloxanes


$(\eta) = 2.15 \cdot 10^{-4} M^{0.65}$. In the second stage, 100 g of α, ω -dioxy polydimethyl siloxane (molecular weight 3300, specific viscosity of the 8% solution: 0.413) and 6.97 g of dibutoxy boron were polycondensed to a gel-like polymer, $[Si(CH_3)_2O]_{44}B(OC_4H_9)_2O$. The complete synthesis can be represented as follows:



X

Polyboron dimethyl siloxanes

S/062/62/000/004/004/013
B110/B101



In the two-stage process, the degree of polymerization of the oligomeric intermediate product is already so high as to render the formation of low-molecular cycles impossible. On heating, tributoxy boron reacts with the oligomer, whereas in the cold it reacts only by

Card 3/5

Polyboron dimethyl siloxanes

S/062/62/000/004/004/013
B110/B101

association. The characteristic viscosity of the reaction mixture of α,ω -dioxo polydimethyl siloxane and tributoxy boron does not increase at 20°C at ratios of 1:1 or 1:2. Measurements of viscosity showed that the removal of the resulting butanol with carbon dioxide accelerated the reaction. After 30-min heating at 200°C, the specific viscosity of the 8% solution increased to 0.946, butanol being obtained in a quantity of 43% of the theoretical amount. The gel-like, polymeric substance, which is soluble in polar and apolar solvents, was also formed after 30-40 min heating at 150°C in vacuo. Its vitrification temperature (-125°C) and yield point (-50°C) were established by thermomechanical investigations. It is elastic on sudden deformation, capable of springbacks on shocks, but flows under slow stress as in the case of polyaluminosiloxanes, coordination bonds are assumed to exist between oxygen and boron atoms in the siloxane chains:

Card 4/5

X

36061

S/079/62/032/004/002/010
D204/D30.

15.8170

AUTHORS: Andrianov, K.A., Zhdanov, A.A., and Odinets, V.A.TITLE: Reactivity of the vinyl group in substituted silanes
in addition reactions with benzene, in the presence
of aluminum chloride

PERIODICAL: Zhurnal obshchey khimii, v. 32, no. 4, 1962, 1126-1130.

TEXT: Addition reactions of C_6H_6 to $CH_2 = CHSiCl_3$ (A), $CH_2 = CHSi(Me)Cl_2$ (B), $CH_2 = CHSi(Me)_2Cl$ (C), and $CH_2 = CHSiMe_3$ (D) were studied, to determine the effect of substituents on the reactivity. All reactions were carried out over 4 1/2 hours at 75°C, in the presence of $AlCl_3$. Additions took place across the double bond to give $PhCH_2CH_2SiCl_3$, $PhCH_2CH_2Si(Me)Cl_2$ and $PhCH_2CH_2Si(Me)_2Cl$ in the cases of A, B and C respectively. The reactivity decreased from A to C and D did not react at all. The reaction mechanism is discussed in terms of displacements of π -electrons of the vinyl group by the Cl and CH_3 groups in compounds A, B, C and D. It is suggested that in Card 1/2

Reactivity of the vinyl group in ...

S/079/62/032/004/002/010
D204/D301

A, the first stage consists of the formation of $\text{CH}_2^+-\text{CH}-\text{SiCl}_3$,



which then reacts with C_6H_6 to give $\text{C}_6\text{H}_5\text{CH}_2\text{CH}_2\text{SiCl}_3 + \text{AlCl}_3$. This is confirmed by the anomalous addition of the aromatic radical to the β -C. Successive replacement of Cl by CH_3 makes the formation of the carbonium ion less probable. Experimental details are fully described and physical properties of the addition products are given. There are 1 table and 5 references: 2 Soviet-bloc and 3 non-Soviet-bloc. The references to the English-language publications read as follows: G.H. Wagner, D.L. Bailey, A.N. Pines, M.L. Dunham and D.B. McIntire, Ind. Eng. Ch., 45, 367, 1953; L.H. Sommer, R.E. VanStrien, F.C. Whitmore, J. Am. Chem. Soc., 71, 3056, 1949; M. Kanazashi, Bull. Chem. Soc. Japan, 1953, 493.

SUBMITTED: April 24, 1961

Card 2/2

37403

S/062/62/000/005/005/008
B110/B101


5.0700
15.9205

AUTHORS: Andrianov, K. A., and Zhdanov, A. A.

TITLE: Synthesis of polyaluminosiloxanes with molecules of a periodic network structure

PERIODICAL: Akademiya nauk SSSR. Izvestiya. Otdeleniye khimicheskikh nauk, no. 5, 1962, 837 - 840

TEXT: The polycondensation of α,ω -dioxypolydimethyl siloxanes (K. A. Andrianov et al. (Dokl. AN SSSR 134, 1347 (1961)) with aluminum butylate was investigated. When the components were in a proportion 3:1, the following reaction took place at 200°C:




In the first stage of polycondensation, the intrinsic viscosity changed very slowly, increasing from 0.052 to 0.092 within 48 hrs. This indicates the formation of a branched oligomer with a central aluminum atom, whereby
Card 1/4

Synthesis of polyaluminorganosiloxanes...

S/062/62/000/005/005/008
B110/B101

viscosity is only slightly increased. A polymer with a periodic network structure, $C_{148}H_{441}O_{74}Si_{72}Al$, is obtained by further heating:




where $D = (CH_3)_2SiO$. This assumption is confirmed by the substantial
Card 2/4

Synthesis of polyaluminosiloxanes ...

S/062/62/000/005/005/008
B110/B101

increase in viscosity from 0.092 to 0.263 during polycondensation for 32 hrs. At a ratio 1:1, linear polycondensation takes place:



This results from the change in viscosity during polycondensation at 180 and 200°C. At 200°C, viscosity rises from 0.092 to 0.164 after polycondensation for 14 hrs, but at a ratio 3:1 this value is only reached after 72 hrs. At room temperature, the 3:1 polymer with an intrinsic viscosity of 0.263 is very elastic, soluble in benzene, toluene, and ether, but becomes insoluble when kept on at a temperature of 200°C. It is elastic over a wide range and has a vitrification temperature of ~-60°C. The high elasticity of its periodic network structure is due to the large spacing of the Al atoms and the considerable flexibility of the polydimethylsiloxane chains. At room temperature, the linear molecule is elastic, readily soluble in organic solvents, and has a wider range of elasticity than the network polymer. There are 3 figures.

Card 3/4

Synthesis of polyaluminorganosiloxanes ... S/062/62/000/005/005/008
B110/B101

ASSOCIATION: Institut elementoorganicheskikh soyedineniy Akademii nauk
SSSR (Institute of Elemental Organic Compounds of the Academy
of Sciences USSR)

SUBMITTED: December 19, 1961

Card 4/4

38718

S/191/62/000/007/005/011
B124/B144

15.8170

AUTHORS: Andrianov, K. A., Zhdanov, A. A.

TITLE: Some peculiarities in the structure of polyorganosiloxanes and polyorganometal siloxanes

PERIODICAL: Plasticheskiye massy, no. 7, 1962, 24-27


TEXT: Problems concerning the structure of polyorganosiloxanes and polyorganometal siloxanes are discussed on the basis of earlier papers by the authors and in publications from the USA. The flexibility of Si-O-Si bonds surrounded by organic groups is proved by the formation of cyclic compounds (e.g. octamethyl cyclotetrasiloxane) in the hydrolysis of aqueous dimethyl dichlorosilane solutions, the size of the resulting ring being dependent on the type of organic groups on the Si atom. Cyclic polymers of the structure

Card 1/6


X

Some peculiarities in the structure ...

S/191/62/000/007/005/011
B124/B144



were also formed in the hydrolysis and cohydrolysis of trifunctional organosilicon monomers (phenyl trichlorosilane) in aqueous solution. A polymer having the structure





Card 2/6


Some peculiarities in the structure ...

S/191/62/000/007/005/011
B124/B144

is formed in the hydrolysis of phenyl trichlorosilane, whereas compounds with the structure



are formed in the hydrolysis of ethyl triethoxy silane and methyl triethoxy silane. Rings of the composition




Card 3/6


Some peculiarities in the structure ...

S/191/62/000/007/005/011
B124/B144

are formed in the synthesis of polymers with inorganic chain molecules by hydrolysis and condensation. Polyalumophenyl- or polyalumoethyl siloxanes:



result from the cohydrolysis of phenyl trichlorosilane or ethyl trichlorosilane with $AlCl_3$, as well as from reactions of $Cl_6H_5Si(OH)_2ONa$ with $Al_2(SO_4)_3$; they are readily soluble in organic solvents and do not melt at $700^\circ C$; their structure may be stated as follows:




Card 4/6

Some peculiarities in the structure ...

S/191/62/000/007/005/011
B124/B144

Polytitanophenyl siloxanes with the structure:



are also formed in the cohydrolysis of phenyl trichlorosilane or phenyl sodium oxydihydroxysilane with TiCl_4 . A similar structure was determined for polytitanoethyl- and polytitanomethyl siloxanes. This also occurred in polyarsenophenyl siloxane of cycloliner structure obtained by cohydrolysis of AsCl_3 and phenyl trichlorosilane, as well as in polyphenyl siloxane synthesized from phenyl trichlorosilane. Thus it has been proved that the synthesis of the polymers here mentioned proceeds via cyclic compounds with functional groups which react with one another to

Card 5/6

Some peculiarities in the structure ...

S/191/62/000/007/005/011
B124/B144

form cycloliner polymers, but steric hindrances caused by organic radicals on the Si atom prevent branching of molecular chains. There is 1 table. The most important English-language references are: M. Id. Sprung, F. O. Guenther, J. Am. Chem. Soc. 77, 6045 (1955); *ibid.* 77, 3996 (1955); B. L. Chamberland, A. G. McDiarmid, *ibid.*, 83, 549 (1961); J. F. Brown et al., *ibid.* 82, 6194 (1960); K. A. Andrianov, J. Polymer Sci. 52, 257 (1961).

X

Card 6/6

ACCESSION NR: AT4033984

S/0000/63/000/000/0045/0052

AUTHOR: Zhdanov, A. A.; Andrianov, K. A.

TITLE: Mechanism of formation of Al containing silicones in the reaction of aluminum butylate with dialkyl (alkyl) diacetoxysilanes

SOURCE: Geterotsepnyye vyssokomolekulyarnyye soyedineniya (Heterochain macromolecular compounds); sbornik statey. Moscow, Izd-vo "Nauka," 1963, 45-52

TOPIC TAGS: aluminum butylate, polymer, silicone, acetoxysilane, butyl acetate, aluminum containing silicone, dimethyldiacetoxysilane, phenylmethyldiacetoxysilane, diethyldiacetoxysilane, trimethylacetoxysilane, polycondensation, heterofunctional polycondensation, acetate group, acetoxy group, butoxy group, polyorganosiloxane

ABSTRACT: Mixtures of aluminum butylate (I; b.p. 296-297C/24 mm) with phenylmethyldiacetoxysilane (II; b.p. 127C/7 mm, acetate group 49.78%), diethyldiacetoxysilane (III; b.p. 95-97C/20 mm; ag 58.52%), dimethyldiacetoxysilane (IV; b.p. 65-67C/20 mm; ag 66.76%) or trimethylacetoxysilane (V; b.p. 102-105C/ag 45.18%) were heated in an oil bath to 200C and kept at that temperature for 30 hours to study the formation of polymers containing the Si-O-Al bond. Reaction with II, III and IV proceeded rapidly at 140-160C, with formation of a polymer product (Al-containing silicone) and precipitation of butyl acetate. Dimethyldibutoxy-

Card 1/2

ACCESSION NR: AT4033984

lane and diethyldibutoxysilane were byproducts of the reactions with III and IV. The reaction pattern followed the mechanism of heterofunctional polycondensation, but also involved an exchange of acetoxy- groups in SI for butoxy- groups. Reaction with V served to demonstrate a dual reactive capability (i.e. the positive charge on the C atom of the carbonyl group increases or decreases). Orig. art. has: 2 tables, 3 graphs, and numerous chemical formulas.

ASSOCIATION: Institut elementoorganicheskikh soyedineniy AN SSSR (Institute of Metalloorganic Compounds AN SSSR)

SUBMITTED: 21May62

DATE ACQ: 30Apr64

ENCL: 00

SUB CODE: OC

NO REF SOV: 006

OTHER: 003

Card 2/2

SECRET

ZHDANOV, A.A., kand.tekhn.nauk

New class of polymers. Priroda 52 no.8:53-55 Ag '63.
(MIRA 16:9)

1. Institut elementoorganicheskikh soyedineniy AN SSSR, Moskva.
(Polymers)

ACCESSION NR: AP4035102

S/0191/64/000/005/0023/0026

AUTHOR: Zhdanov, A. A.; Andrianov, K. A.; Baksheyeva, T. S.; Polikanin, N. A.; Levitskiy, M. M.

TITLE: Investigation of the properties of organosilicon polymers containing hydroxyphenyl groups.

SOURCE: Plasticheskiye massy*, no. 5, 1964, 23-26



TOPIC TAGS: organosilicon polymer, hydroxyphenyl containing siloxane, ester interchange reaction, polymer chain growth, diphenylolpropane, polyphenylbutoxy-siloxane, diene reaction product, molded composition, physical property, mechanical property, cross linkage, polymerization

ABSTRACT: The reaction of forming organosilicon compounds containing the hydroxyphenyl group, and the properties of the product polymers were investigated. The hydroxyphenyl group can be introduced into the siloxane chain by ester interchange of the diphenylolpropane (diene) with organosilicon polymers or oligomers containing butoxy groups on the silicon atom. If the oligomer has only terminal butoxy groups the product formed will have diene groups at the ends of the chain. If the

Card 1/3

ACCESSION NR: AP4035102

butoxy groups are also on the side chain of the organosilicon polymer, the product will contain the diene group in each link of the polymer chain. The composition and properties of the end products are determined by the molecular ratio of the reagents. With a 1:1 ratio of diene: α, ω -dibutoxypolydimethylsiloxane a linear polymer is formed with blocks of the organosilicon molecules joined by the diene:



where R = CH₃ or C₆H₅.

With a 2:1 ratio, the oligomer formed contains terminal diene groups:
 $\text{HO} \text{C}_6\text{H}_4 \text{C}(\text{CH}_3)_2 \text{C}_6\text{H}_4 \text{O} \left[\text{SiR}_2\text{O} \right]_n \text{C}_6\text{H}_4 \text{C}(\text{CH}_3)_2 \text{C}_6\text{H}_4 \text{OH}$.

Card 2/3

ACCESSION NR: AP4035102

Using the product of the 2:1 reagent ratio there is no viscosity change in going from the dimer to the tetramer, but in the 1:1 product the viscosity increases indicating growth of the polymer chain. When the polymer formed by reaction of polyphenylbutoxysiloxane with diane is completely polymerized (in 8-25 minutes) the product is fusible and soluble; when the polymethylbutoxysiloxane-diane reaction product is polymerized to 60-70% it gels, indicating crosslinkage. Molded fiberglass compositions containing 32% of these polymers were formed at 250-300 kgs/cm² at 145-150C, 1.5-2 min/mm and cured at 160C for 6-7 hours. Their physical and mechanical properties are tabulated. Orig. art. has: 4 tables, 4 figures and 3 equations.

ASSOCIATION: None

SUBMITTED: 00

ENCL: 00

SUB CODE: 00

NO REF SOV: 001

OTHER: 000

Card 3/3

WRITE BELOW THIS LINE

ACCESSION NR: AP4037291

S/0190/64/006/005/0940/0944

AUTHOR: Zhdanov, A. A.; Andrianov, K. A.; Kazakova, A. A.;
Baksheyeva, T. S.

TITLE: Polymers with inorganic backbones. Synthesis of polyorgano-
phosphoroaluminoxanes

SOURCE: Vy*sokomolekulyarny*ye soedineniya, v. 6, no. 5, 1964,
940-944


TOPIC TAGS: polymers, inorganic backbone containing polymer, phos-
phorus containing polymer, aluminum containing polymer, aluminoxane,
polyorganophosphoroaluminoxane, aluminum containing polymethylphos-
phonate, aluminum ethylate, aluminum butylate, diethyl methylphos-
phonate, dibutyl methylphosphonate, diphenyl methylphosphonate,
polycondensation, methylphosphonyl chloride

ABSTRACT: The reaction of aluminum alcoholates with some deriva-
tives of methylphosphonic acid, and the properties of the condensa-
tion products obtained have been studied. Aluminum ethylate or


Card 1/3

ACCESSION NR: AP4037291

aluminum butylate was condensed with either methylphosphonyl chloride or diethyl, dibutyl, or diphenyl methylphosphonate. Solid polymers obtained in the process of the progressing condensation contained the group



and, if methylphosphonate chloride was used, the group



Card 2/3